



**SIRIM QAS International Sdn. Bhd.**

No. 1, Persiaran Dato' Menteri, P.O.Box 7035, Seksyen 2, 40911 Shah Alam, Selangor Darul Ehsan

MALAYSIA

Tel: 03-55446465

Fax: 03-55446454

http: //www.sirim.my

(Company No: 410334-X)

**TEST REPORT**

**REPORT NO.: 2005FE0303**

**PAGE 1 OF 3**

This Test Report refers only to samples submitted by the applicant to SIRIM QAS International Sdn. Bhd. and tested by SIRIM QAS International Sdn. Bhd. This Test Report shall not be reproduced, except in full and shall not be used for advertising purposes by any means or forms without written approval from Executive Director of SIRIM QAS International Sdn. Bhd. Please refer overleaf for conditions to the use of Test Report.

Our Ref : SQAS / FET / 15 / 1 - 6

Issued by : **Fire Engineering Testing Section**

Issued date : **28 NOV 2005**

Product : **PREPAINTED GALVANIZED STEEL SHEET**

Reference Standard/ Method of test : BS 476 : Part 7: 1997  
Fire Test on Building Materials and Structures  
Part 7: Surface Spread of Flame Test.

Applicant : **Group Steel (M) Sdn.Bhd.**  
180, Kawasan Industri Ayer Keroh,  
75450 Ayer Keroh,  
Melaka.  
(Attn: Mr. Lew Ren Shang)


Description of sample : 6 pieces of Prepainted Galvanized Steel Sheet.  
Size of Specimen : 270mm × 885mm × 0.28mm (measured thickness)  
Nominal Thickness : 0.26mm  
Density : 7908 kg/m<sup>3</sup>


The specimens were tested with the **Prepainted** face side exposed to the specified heating conditions of the fire test.

Date received : 17.11.2005

Job No. : J2005 506 0270

  
.....  
**HISYAM HISHAMUDDIN**  
Technical Executive



  
.....  
**ROHAYA IBRAHIM**  
Senior Manager  
Fire Engineering Testing Section  
Testing Services Department  
SIRIM QAS International Sdn. Bhd.

# TEST REPORT

REPORT NO.: 2005FE0303

PAGE 2 OF 3

This Test Report refers only to samples submitted by the applicant to SIRIM QAS International Sdn. Bhd. and tested by SIRIM QAS International Sdn. Bhd. This Test Report shall not be reproduced, except in full and shall not be used for advertising purposes by any means or forms without written approval from Executive Director of SIRIM QAS International Sdn. Bhd.


**Name of Applicant** : Group Steel (M) Sdn.Bhd.  
**Product** : Prepainted Galvanized Steel Sheet  
**Nominal Thickness** : 0.26mm  
**Measured Thickness** : 0.28mm  
**Density** : 7908 kg/m<sup>3</sup>

## Requirement

The flame spread on any specimen of the sample shall not exceed the limit assigned for the class with the proviso that for one specimen only in the sample the flame spread may exceed this limit by the tolerance shown.

## Classification of Surface Spread of Flame

Classification	Flame Spread at 1½ min		Final Flame Spread	
	Limit (mm)	Tolerance for one specimen in sample (mm)	Limit (mm)	Tolerance for one specimen in sample (mm)
Class 1	165	25	165	25
Class 2	215	25	455	45
Class 3	265	25	710	75
Class 4	Exceeding Class 3 limits			



28 NOV 2005

## TEST REPORT

**REPORT NO.:** 2005FE0303

**PAGE 3 OF 3**

This Test Report refers only to samples submitted by the applicant to SIRIM QAS International Sdn. Bhd. and tested by SIRIM QAS International Sdn. Bhd. This Test Report shall not be reproduced, except in full and shall not be used for advertising purposes by any means or forms without written approval from Executive Director of SIRIM QAS International Sdn. Bhd.

### Test Results


**Product** : Prepainted Galvanized Steel Sheet      **Density** : 7908 kg/m<sup>3</sup>  
**Nominal Thickness** : 0.26mm      **Date of Test** : 24.11.2005  
**Measured Thickness** : 0.28mm

Specimen No.	1	2	3	4	5	6
Spread of flame at 1½ minutes (mm)	0	0	0	0	0	0
Distance (mm)	Time of spread of flame to indicated distance ( minutes . seconds )					
75	-	-	-	-	-	-
165	-	-	-	-	-	-
190	-	-	-	-	-	-
215	-	-	-	-	-	-
240	-	-	-	-	-	-
265	-	-	-	-	-	-
290	-	-	-	-	-	-
375	-	-	-	-	-	-
455	-	-	-	-	-	-
500	-	-	-	-	-	-
525	-	-	-	-	-	-
600	-	-	-	-	-	-
675	-	-	-	-	-	-
710	-	-	-	-	-	-
750	-	-	-	-	-	-
785	-	-	-	-	-	-
825	-	-	-	-	-	-
865	-	-	-	-	-	-
Time of maximum spread of flame (minutes . seconds)	-	-	-	-	-	-
Distance of maximum spread of flame (mm)	0	0	0	0	0	0

### Conclusion

In accordance with the class definition specified in the standard, the test results show that the sample tested has a Class **One** Surface Spread of Flame.

The test results relate only to the behaviour of the test specimens of a product under the particular conditions of test; they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.



28 NOV 2005