

SIRIM QAS International Sdn. Bhd.

No. 1, Persiaran Dato' Menteri, P.O.Box 7035, Seksyen 2, 40911 Shah Alam, Selangor Darul Ehsan MALAYSIA

Tel: 03-55446465

(Company No: 410334-X)

Fax: 03-55446454

http://www.sirim.mv

### **TEST REPORT**

REPORT NO.: 2010FE0187 **PAGE OF** 3

This Test Report refers only to samples submitted by the applicant to SIRIM QAS International Sdn. Bhd. and tested by SIRIM QAS International Sdn. Bhd. This Test Report shall not be reproduced, except in full and shall not be used for advertising purposes by any means or forms without written approval from Managing Director of SIRIM QAS International Sdn. Bhd. Please refer overleaf for conditions to the use of Test Report.

Our Ref

SQAS/FPS/15/1-6

Issued by

**Fire Protection Section** 

Issued date

21 MAY 2010

Product

**GALVANIZED IRON SHEET (BMT 0.35 MM)** 

Reference Standard/

BS 476: Part 7: 1997

Method of test

Fire Test on Building Materials and Structures

Part 7: Surface Spread of Flame Test.

Applicant

CSC STEEL SDN. BHD.

180, Kawasan Industri Ayer Keroh,

Ayer Keroh, 75450 Melaka.

(Attn: Mr. Chan Hian How)

Description of sample

6 pieces of Galvanized Iron Sheets.

Size of Specimen

: 270 mm × 885 mm × 0.35 mm (Measured thickness)

Nominal Thickness

BMT  $0.35 \text{ mm} \pm 0.03 \text{ mm}$ 

Nominal Density

 $7850 \text{ kg/m}^3 \pm 10\%$ 

Measured Density

 $8061 \text{ kg/m}^3$ 

The specimens were tested with the face side exposed to the specified heating

condition of the fire test.

Date received

03.03.2010

Job No.

J20105060092

WAN MỢHD KHAIRI WAN YAHYA Testing Executive

**FROTECTION** 

ZAHNI AHMAD

Group Leader Fire Protection Section

Testing Services Department SIRIM QAS International Sdn. Bhd.

## **TEST REPORT**

REPORT NO.: 2010FE0187

PAGE 2 OF 3

This Test Report refers only to samples submitted by the applicant to SIRIM QAS International Sdn. Bhd. and tested by SIRIM QAS International Sdn. Bhd. This Test Report shall not be reproduced, except in full and shall not be used for advertising purposes by any means or forms without written approval from Managing Director of SIRIM QAS International Sdn. Bhd.

Name of Applicant

: CSC STEEL SDN. BHD.

Product

Galvanized Iron Sheet (BMT 0.35 mm)

Nominal Thickness

: BMT  $0.35 \text{ mm} \pm 0.3 \text{ mm}$ 

Nominal Density

 $7850 \text{ kg/m}^3 \pm 10\%$ 

Measured Density

8061kg/m<sup>3</sup>

Measured Thickness

0.35 mm

Date of Test

06.05.2010

#### Requirement

The flame spread on any specimen of the sample shall not exceed the limit assigned for the class with the proviso that for one specimen only in the sample the flame spread may exceed this limit by the tolerance shown.

Classification of Surface Spread of Flame

Classification	Flam	e Spread at 1½ min	Final Flame Spread		
	Limit (mm)	Tolerance for one specimen in sample (mm)	Limit (mm)	Tolerance for one specimen in sample (mm)	
Class 1	165	25	165	25	
Class 2	215	25	455	45	
Class 3	265	25	710	75	
Class 4		Exceeding Class	3 limits		



# TEST REPORT

**REPORT NO.:** 

2010FE0187

PAGE

OF

3

3

This Test Report refers only to samples submitted by the applicant to SIRIM QAS International Sdn. Bhd. and tested by SIRIM QAS International Sdn. Bhd. This Test Report shall not be reproduced, except in full and shall not be used for advertising purposes by any means or forms without written approval from Managing Director of SIRIM QAS International Sdn. Bhd.

**Test Results** 

**Product** 

Galvanized Iron Sheet (BMT 0.35 mm)

Measured Thickness

: 0.35 mm

Density

8061 kg/m<sup>3</sup>

Date of Test

: 06.05.2010

Specimen No.	1	2	3	4	5	6			
Spread of flame at 1½ minutes (mm)	0	0	0	0	0	0			
Distance (mm)	Time of spread of flame to indicated distance (minutes . seconds)								
75	-	-	_	_	_	Ι .			
165	_	_	-	_	_				
190	_	-	-	_		_			
215	-	_	_	_	_	_			
240	_	-	_	-	_	_			
265	_		_	_	_	_			
290	-	_	_	_	<u> </u>	_			
375	_	_	_	_	_	_			
455	-	_	_	_	_	_			
500		_	_	_	_	_			
525		_	_	_	_				
600	_	-	<b>-</b>	_	-	_			
675		-	_	_	_	_			
710	_	-	_	_	ļ. <u>.</u>	_			
750	-	-	_	_	_	_			
785	-	<u> </u>	_	_	_	_			
825	-	-	_	<u>-</u>		_			
865	· •	_	-	_	_	_			
Time of maximum									
spread of flame	-		-	-	_	_			
(minutes . seconds)	· · · · · · · · · · · · · · · · · · ·								
Distance of	0		^	,					
maximum spread of flame (mm)	0	0	0	0	0	0			

#### Conclusion

In accordance with the class definition specified in the standard, the test results show that the sample tested has a Class <u>One</u> Surface Spread of Flame.

The test results relate only to the behaviour of the test specimens of a product under the particular conditions of test; they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

