

### **ABOUT US**

CSC Steel (CSCM) is a Taiwanese-owned steel producer that specialises in galvanised steel products and colour-coated steel products for the building material industry under our proprietary brand names, realzinc™ and realcolor®. We also produce pickled & oiled steel coils and cold-rolled steel coils.

Incorporated in Malaysia, we have been listed on the Main Board of Bursa Malaysia since 2004. By leveraging on the management experience and technological expertise of our major shareholder, China Steel Corporation of Taiwan, we are committed to providing our customers with high-quality products and value-added services.

For product identification and originality, please check the reverse side of the coil for the following branding text.

realcolor (R) CAHAYA made by CSC Steel YYYYMMDD TTTT

#### RELIABLE | EXPERIENCED | ACCOUNTABLE | LONG LASTING











RECYCLABLE



CSC STEEL HOLDINGS BERHAD CSC STEEL SDN BHD

180, Kawasan Industri Ayer Keroh, Ayer Keroh, 75450 Melaka, Malaysia. **T:** 606 231 0169 (Hunting) **F:** 606 231 0167/9166 **E:** sales@cscmalaysia.com (Sales)
















**BACK COVER FRONT COVER** 

# **REALCOLOR® CAHAYA**

Realcolor Cahaya provides colour selections for roofing and cladding applications with excellent surface hardness, flexibility and vibrant protection. Stylish pre-painted roofing and cladding solutions protect your home against the environment.


### **ADVANTAGES**

- Corrosion resistance
- Colour options
- Durability
- Good formability
- Affordable
- Warranty up to 5 years against perforation



### **END USAGES**

Generally used in architectural structures such as roofing, wall cladding, fencing, panels and advertising boards.



## **SECTIONAL VIEW OF COATED STEEL**

Pre-painted galvanised steel (PPGI) is a type of colour-coated steel that is generally used in exterior architectural structures and building materials such as roofing, wall cladding, fencing, wall panels and advertising boards.

# **TYPICAL PROPERTIES**

Test	Result	Method/Remark
1031	HOSUIT	Wethod/Hemark
T-Bend	5T max	
Pencil Hardness	F-2H	Mitsubishi-uni
Cross-Hatch	100/100	
Solvent Resistance	≥ 100DR For MEK DR	
Erichsen Cupping Test	30mm for SQ,	
	50mm for CQ	
Reverse Impact	10 Joules	No loss of adhesion
Salt Spray Test	500 hrs	MS 133 : Part H8, Part E6, Part H2
		Undercut at scribes lines/ loss of adhesion/blistering, 2-S3/ corrosion at base metal
QUV-A	1000 hrs	Gloss retention > 80%
		Average colour change not more than 2 dE units (CIELab)



Standard		Steel Grade
MS 2383		01, 250, 280, 320, 350, 550
JIS G3312		CGCH, CGCC, CGC340, CGC400, CGC440, CGC570
Thickness (mm)	:	0.176 ~ 0.30 (BMT)
Width (mm)	:	1,250 (Maximum)
Zinc Coating	:	Z080 (Z08)
Top Coat DFT	:	10/2
MS 2383 Class	:	C2



INSIDE 1 INSIDE 2